

## Technical Datasheet - METYX Composite Reinforcements

PRODUCT CODE	5200.004.004
PRODUCT NAME	Q1200E10A
PRODUCT DESCRIPTION	0/45/90/45 QUADRAXIAL EGLASS
CUSTOMER CODE	.
CUSTOMER ID	.

REINFORCEMENT CONSTRUCTION		
LAYER	FIBER TYPE	AREA WEIGHT
1	0°	600 Tex
2	45	300+600 Tex
3	90	600 Tex
4	-45	300+600 Tex
5	Stitch	76 Dtex
6		
7		

\* Checked via own test based on ISO 3374.

**TOTAL\*** 1200 gr / m2 ( ± %3 )

OTHER PROPERTIES		ROLL INFO	
Stitch Gauge	10 stitches/inch	Roll Width	127 cm
Stitch Type	Pillar-Tricot	Roll Weight	68 kg
Stitch Length	3 mm	Roll Length	45 m
Pilot Yarn / Position	--- / ---	Core Diameter	76 mm

Resin Compatibility	Loss on Ignition	Moisture Content
Polyester, Vinylester, Epoxy resins	Max.%0,55 by weight (ISO 1887)	Max.%0,20 by weight (ISO 3344)

Packaging	All rolls are wrapped with polyethylene bags; placed in pallet boxes or in single cardboard boxes or in pyramid style on pallets.
Labelling	Each roll is labelled on the inner side of the core, on the bag or on the cardboard boxes including a unique reference number for its traceability.
Storage	Store at %40-70 relative humidity and 18-30 °C temperature range. Recommended to be brought to working area 24 hrs prior to use.

Certification	DNV	Lloyd's Register
All Metyx reinforcements are produced & handled in ISO 9001:2000 System	TYPE Approved	—

**Note:** The above specifications reflect the product data on release date but are subject to change without prior notice.

**Address:**  
Orhanli Beldesi 34956  
Tuzla Istanbul – TURKIYE



**Phone :** +90-216-394-32-60  
**Fax :** +90-216-394-32-58  
**Web :** www.metyx.com